

SYNTHESIS AND CHARACTERIZATION OF CO-POLYMER AND SUBSTITUTED WITH  
AMINO DRUG<sup>1</sup>\*Mohammed A. Farhan, <sup>2</sup>Nuha F. Abdul Kareem and <sup>3</sup>Assmaa A. Hasan<sup>1,2</sup>Diyala University, College of Science, Department of Chemistry, Diyala, Iraq.<sup>3</sup>Diyala University, College of Science, Department of Biology, Diyala, Iraq.**\*Corresponding Author: Mohammed A. Farhan**

Diyala University, College of Science, Department of Chemistry, Diyala, Iraq.

Article Received on 04/10/2017

Article Revised on 25/10/2017

Article Accepted on 14/11/2017

**ABSTRACT**

In this research the structural modification of starch was carried out with methyl nadic anhydride (H) as a spacer by using ceric ammonium nitrate (CAN) as an initiator, and grafted copolymer was substituted with amino drug procaine (HB), this design of carries for controlled delivery of therapeutic agent which could release the entrapped drug over an extended period of time, due to its non toxic, biodegradable and slow digesting nature, the new drug copolymer was characterized by FTIR, <sup>1</sup>H-NMR and UV Spectroscopes, Thermal analysis was studied. The prepared drug copolymer was analyzed in different pH values at (37 °C) as in vitro study and controlled drug release was compared at zero time and after four days..

**KEYWORDS:** starch, methyl nadic anhydride, Procaine, Copolymer, Drug Copolymer.**INTRODUCTION**

Starch is a valuable ingredient in the food industry, it serves not only as a nutrient source for food, but also as a thickener, a binding agent, a texturizer, a filler and a film forming agent in the food industry. A selection of starch varieties for different food products depends on starch functional properties, including viscosity, shear resistance, gelatinization properties, textures, solubility, tackiness and gel stability. These functional properties are determined by the chemical structures of starch.<sup>[1]</sup> Grafted copolymerization of unsaturated monomer on to natural polymers such as starch (starch-graft-copolymers), the side chains of a given monomer are attached to the main chain of starch. Acrylic/vinyl monomers are usually used for grafting onto starch, which include acrylamide, acrylic acid, acrylonitrile, methacryl amide, methacrylic acid, vinyl acetate, methacrylonitrile.<sup>[2,3]</sup> to add new properties and more attention tissue engineering and tissues adhere<sup>[4-6]</sup> It can be used for the production of biocompatible materials in the pharmaceutical and medical applications.<sup>[7]</sup> The hydrophilic monomers which grafted on surface of polymers are biodegradable and sensitive to stimuli pH and temperature.<sup>[8]</sup> The biodegradable property makes it possible to implant them into the body without the need of subsequent removal by the surgical operation. Drugs formulated with these polymers can be released in a controlled manner, by which the drug concentration in the target site is enhanced. The release rates of the drugs from biodegradable polymers can be controlled by a number of factors, such as biodegradation kinetics of the

polymers<sup>[9, 10]</sup>, grafted copolymer was substituted with procaine as antibiotics.

Procaine is a white powder with Molecular formula (C<sub>13</sub>H<sub>20</sub>N<sub>2</sub>O<sub>2</sub>), and molecular weight (236.3 gm/mole), it like other local anesthetics such as tetra caine acts as a nerve block, halting the generation and conduction of nerve impulses signal pain, it has four to six times less toxic than cocaine, it is also used in obstetrics and some times for relief pain in the lower back and tooth extraction<sup>[11]</sup>, and it is useful for treating bacterial (as an antibacterial drug) and parasitic infections.<sup>[12]</sup> The main objective of the research is to modified and study starch which was grafted with methyl nadic anhydrides, then the grafted anhydride was substituted by procaine to gain combinatorial and new properties of natural polymer. This work aimed to preparation of new procaine copolymer to enhance the sustained release throw long period, also to minimize the some side effect of this drug.

**Experimental  
Instrumentation**

Melting points were measured using Thermal Microscope (Kofler-method), and Reichert thermovar, Stuart SMP 30. Infrared spectrophotometer measurements were performed using Shimadzu FT-IR 8400 series Fourier Transform, <sup>1</sup>H-NMR spectra were measured with a bruker spectrophotometer model ultra-shield at 300.13 MHz in DMSO-d<sub>6</sub>, U.V-Visible double beam scanning spectrophotometer VARIAN (UV-Vis)-100 Conc, at room temperature. All chemicals were

purchased from Fluka and BDH; all the available chemical reagents were used without further purification.


#### A- Preparation of starch grafted methyl nadic anhydride (H)

(1.0 gm) of starch dissolved in (25ml) of acetone, (0.1gm) (1ml) of ceric ammonium nitrate solution (CAN), (1gm) of methyl nadic anhydride (MNA) was added, the mixture was introduced in polymerization bottle, the mixture was heated about (30) minutes at (60 °C), using water bath, the green color product was produced (90%), S.P (86-92 °C).

#### B-Substituted of (H) with procaine

(0.2 gm) of starch- g-methyl nadic anhydride (H) was dispersed in (5ml) of acetone, (0.1 gm) of procaine dissolved in (5ml) of dioxane, (0.5 ml) of DMF was added to the mixture, the mixture was refluxed with stirring about 1 hour at (90 °C), the colored solution was filtered, the filtrate was isolated and the solvent was evaporated, the black product was washed with di ethyl ether two times and dried at (50 °C) in a vacuum, conversion (92%). S. p. (210-220 °C). all physical properties were listed in table (1).

**Table 1: Physical properties of prepared Polymer (HB).**

Pol.	-Drugs	Color	Softening point °C	Conversion ratio %
HB	 Procaine	Light brown	210-220	92



### RESULT AND DISCUSSION

Starch can be grafted as main chain of backbone of polymer, it was polymerized and initiated by various initiators.<sup>[13]</sup> Among the various types of initiators, ceric ion offers many advantages because of its high grafting efficiency. when (Ce<sup>+4</sup>) salts such as cerium ammonium nitrate (CAN) is used as initiator in the grafting of vinyl monomers onto glucose, at first a ceric ion-glucose


complex occurs, and then it decomposes to cerous (Ce<sup>+3</sup>) ion.<sup>[14]</sup> and glucose radicals created by hydrogen abstraction from glucose. Thus, The radical formation on the glucose backbone occur on the oxygen atom.<sup>[15, 16]</sup> The -OH group present on the backbone of starch polymer acts as the active sites for the graft copolymerization

The mechanism of grafting monomer onto starch as shown below in equations(1).


\* Initiation:



\* Propagation:




\* Termination:



#### Scheme (1): The mechanism of grafting reaction of monomer onto starch by CAN.

Graft co polymer was prepared by the reaction of starch with methyl nadic anhydride by using ceric ammonium nitrate as a radical initiator. new drug polymer was


prepared by the reaction of starch with methyl nadic anhydride and substituted with procaine in reaction below.



**Scheme (2): starch-g- methyl nadic anhydride and Substituted it with procaine.**

The presence of  $-\text{NH}_2$  group in the drug, which acts as strong nucleophile attack on the  $\text{C}=\text{O}$  group of methyl nadic anhydride produced N-drug substituted, the

mechanism of reaction was described as shown below.<sup>[17]</sup>



**Scheme (3): Mechanism of ring opening reaction of Starch -g- Methyl nadic anhydride by nucleophilic reaction.**

Figure (1) FTIR spectrum of natural polymer (starch) showed absorption peaks at  $(3290\text{ cm}^{-1})$  of (O-H) group and (C-O-C) ether absorption peak at  $(1012-1149\text{ cm}^{-1})$ , peak at  $(2928)\text{ cm}^{-1}$  due to (C-H aliphatic) stretching.


Figure (2) FTIR spectrum of (H) starch grafted Methyl nadic anhydride gave the characteristic absorption of carbonyl group of anhydride peak was appeared at  $(1776\text{ and }1855\text{ cm}^{-1})$  in addition to the starch backbone absorptions.

Figure (3) FT-IR spectrum of prepared compound[HB] showed absorption band at  $(3227)\text{ cm}^{-1}$  due to (NH) stretching, and  $(1651)\text{ cm}^{-1}$  due to (C=O amide) stretching, and  $(1602)\text{ cm}^{-1}$  due to (NH) bending, peak at  $(1705)\text{ cm}^{-1}$  correlated to (C=O) stretching vibration of acid. Other bands of the compounds are listed in Table (2).

**Table 2: FT-IR absorptions of grafted natural polymers (Starch) with anhydrides and substituted with drug compound (Procaine).[HB]**

Comp No.	$\nu$ (O-H) $\text{cm}^{-1}$ alcohol	$\nu$ (N-H) $\text{cm}^{-1}$ amide	$\nu$ (C=O) $\text{cm}^{-1}$ amide	$\nu$ (C=C) $\text{cm}^{-1}$ Aromatic	$\nu$ (C-H) $\text{cm}^{-1}$ Aromatic	$\nu$ (C-O) $\text{cm}^{-1}$ acid	$\nu$ (C=O) $\text{cm}^{-1}$ carboxylic	$\nu$ (O-H) $\text{cm}^{-1}$ carboxylic	$\nu$ (C-N) $\text{cm}^{-1}$	$\nu$ (C-O-C) $\text{cm}^{-1}$ Ether	$\nu$ (C-H) $\text{cm}^{-1}$ aliphatic	$\nu$ other band $\text{cm}^{-1}$
starch	3290 broad	-	-	-	-	-	-	-	-	1012-1149 Strong	2928, 2852	-
H	3180	-	-	-	-	-	1703	2400-3500 Very broad	-	1080-1217 Strong	2968, 2872	Anhydride 1776-1855 Strong
HB	3354	3227	1651 Strong	1519	3086	1271 Strong	1705	2400-3500 Very broad	1311 medium	1001-1170 Strong	2874, 2933	1602 -NH bending

$^1\text{H-NMR}$  spectra of [HB] polymer was obtained using  $\text{DMSO-d}_6$  as a solvent with TMS as internal standard. The  $^1\text{H-NMR}$  spectrum of drug polymer [HB] showed in figure (4). indicated the signal assignments in the corresponding formula, which showed the following signals.




### Structure of HB

0.85 ppm (Singlet, 3H,  $\text{CH}_3$ ) for ring methyl nadic, 1.24 ppm (Triplet, 6H,  $2\text{CH}_3$ ), 1.4 ppm (Triplet, 2H,  $\text{CH}_2$ ) for


ring methyl nadic, 2.2 ppm (Triplet, 2H,  $\text{CH}_2\text{-N}$ ), 3.19 ppm (quartet, 4H,  $2\text{CH}_2$ ), 3.5 ppm (doublet, 1H,  $\text{CH-O-starch}$ ), 4.5 ppm, (Triplet, 2H,  $\text{COO-CH}_2$ ), 5.7 ppm (Singlet, 1H, OH for starch), 6.5-7.7 ppm (Multiple, 4H, Ar-H), 8 ppm (Singlet, 1H,  $\text{CO-NH}$  amide), 12.0 ppm (Singlet, 1H,  $\text{COOH}$ ).

### Controlled drug release

Release of (HB) was studied, (100 mg) was added continuously in (100 ml) buffer solution at ( $37^\circ\text{C}$ ). the wave length of  $\lambda_{\text{max}}$  was measured at different periods and different pH values (1.1 -7.4) by using UV spectrometer. These samples were analyzer by UV-spectroscopes periodically withdrawn for every days, it was appeared the sustained release by measuring the mole fraction were constructed from UV. indicated the rate of hydrolysis in basic medium is higher than acidic medium. Mechanism of these drug polymer were illustrated as shown in the scheme (4,5).



**Scheme (4): Mechanism of hydrolysis drug polymer in acidic medium.**



**Scheme (5): Mechanism of hydrolysis drug polymer in basic medium.**

It was found the controlled drug release was hydrolysis of amide group through four days in basic medium, but it was higher hydrolysis in basic medium than acidic medium.

**Thermal Properties of polymer drug<sup>[14]</sup>**


Thermal stability of prepared polymers were investigated by (TGA and DSC) Table (3) TGA showed the results of some prepared drug polymers which indicated the high thermal resistance and showed their steps of weight loss-temperature. This high thermal resistance indicated the high interaction between amide hydrogen bonding through the polymer chains and led to best sustain drug

release. Several thermal stability parameters were determined from TGA curve as shown in table (3).

**Table (3): TGA Analysis of some polymer drugs.**

No. drug polymer	Temperature	Losses weight%
H	123, 318, 404	3, 58, 38
HB	212, 283, 480	13, 26, 48

It was concluded that the thermal stability of drug polymer was more than the drug alone this cause more expire date and more protection of the drug satiability.



**Figure (1): FTIR spectrum of starch.**




Figure (2): FTIR spectrum of starch-g-methyl nadic anhydride (H).




Figure (3): FTIR spectrum of starch-g-methyl nadic anhydride (HB).




Figure (4): <sup>1</sup>H-NMR Spectrum of HB.




Figure (5): UV Spectra hydrolysis of HB in pH7.4.




Fig (6): DSC and TGA Analysis of H.




Fig (7): DSC and TGA Analysis of HB

## REFERENCES

1. Li Li, A thesis, Starch biogenesis relationship between starch structures and starch biosynthetic enzymes, Iowa State University, 2006.
2. Suda K., Kanlaya M., Manit S., Synthesis and property characterization of cassava starch grafted poly[acrylamide-co-(maleic acid)] superabsorbent via  $\gamma$ - irradiation. *Polymer*, 2002; 43: 3915–3924.
3. Vandana S., Ashutosh T., Sadanand P., Somit K.S., Microwave-accelerated Synthesis and Characterization of Potato Starch-g-poly(acrylamide), *Starch/Strke*, 2006; 58: 536–543.
4. Athawale VD and Lele V Thermal studies on granular maize starch and its graft copolymers with vinyl monomers. *Starch/Starke*, 2000; 52: 205–213.
5. Cha JN, Stucky GD, Morse DE, Deming TJ Biomimetic synthesis of ordered silica structures mediated by block copolypeptides. *Nature*, 2000; 403: 289–292.
6. van Hest JCM, Tirrell DA Protein-based materials, toward a new level of structural control. *Chem Commun*, 2001; 1897–1904.
7. Prashant PK, Vivek BR, Deepashree ND, Pranav PP. Hydrogels as a drug delivery system and applications: a review. *Int J Pharm Pharm Sci*. 2012; 4: 1-7. 5-. Bishop PN. Structural macromolecules and supramolecular organisation of the vitreous gel. *Progress in Retinal and Eye Research*, 2000; 19: 323-344.
8. Zentner GM, Rathi R, Shih C, McRea JC, Seo MH, Oh H, Rhee BG, Mestecky J, Moldoveanu Z, Morgan M, Weitman S Biodegradable block copolymers for delivery of proteins and water-insoluble drugs. *J Control Release*, 2001; 72: 203–215.
9. Al-Sabagh A, Noor MR, Din EL, Morsi RE, Elsabee MZ Styrene-maleic anhydride copolymers esters as flow improvers of waxy crude oil. *J Pet Sci Eng*, 2009; 62: 139–146.
10. Zhu LP, Yi Z, Liu F, Wei XZ, Zhu BK, Xu YY Amphiphilic graft copolymers based on ultrahigh molecular weight poly(styrene-alt-maleic anhydride) with poly(ethylene glycol) side chain for surface modification of polyethersulfone membranes. *Eur Polym J*, 2008; 44: 1907–1914.
11. Mouyed Q. Al-Abachi, Wasan A. Al-Uzri, Hind S. Al-Ward, Batch and Flow-Injection Spectrophotometric Determination of Procaine HCl in Pharmaceutical Preparations Via Using Diazotization and Coupling Reaction, *J. Baghdad for Sci*, 2012; 9(3).
12. David G Watson, *Pharmaceutical Chemistry*, University of Strathclyde, Glasgow, UK, 2011.
13. Isam Y. M., Fakhru'l- Razi A., Suleyman A., Mansor B., Rahman A., Yunus W. M. Z., (Preparation and characterization of poly(methylmethacrylate) grafted sago starch using potassium persulfate as redox initiator), *Journal of Applied Polymer Science*, 2004; 94(5): 1891-1897.
14. Ahlam Ahmed Frayyih AL-Shihani, A thesis, Synthesis and Characterization of Graft Copolymers as Fillers of Dentistry, Al-mustansiriyah University, Iraq, 2016.
15. Susheel Kalia<sup>1</sup>, M.W. Sabaa<sup>2</sup>, Polysaccharide Based Graft Copolymers, <sup>1</sup>Dept. of Chemistry, Bahra University, India, <sup>2</sup>Faculty of Science Cairo University, Egypt, New York, 2013.
16. Nguyen T.T, nguyen V., KINETICS AND MECHANISM OF GRAFT POLYMERIZATION OF ACRYLIC ACID ONTO STARCH INITIATED WITH CERIC AMMONIUM NITRATE, *Journal of Chemistry*, 2010; 48(5): 621–626.
17. Firyal M.Ali Sana .H.Awad\* Mena. M. Hamid, Synthesis of Substituted Gelatine Grafted Maleic Anhydride as Drug Copolymer, *Chemistry and Materials Research*, 2015; 7(5): 1-8.